



Sogivaswiss SA
Ch. de Lavasson 8
1196 Gland
Switzerland

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
ProductTesting-GA@eurofins.com
www.eurofins.com/product-emissions

Date
13 August 2014
Our ref.
392-2014-00095703C

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

Sample identification	N/A
Product type	Metolux
Product data, according to manufacturer	Density: 1.67 g/ml at 20 °C ** Water content: 0 g/l** Exempt compounds: none ***
Date received	28 May 2014
Analytical period	30 May 2014 – 10 June 2014

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U _m (%)
LEED 2009 EQ c4.1 (Modified)	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %
<p>20 cm sample was dispensed and discarded. Further sample was dispensed in a preweighed dish and allowed to sit for 1 hour (durometer reading > 80). Volatile content of the sample was determined gravimetrically by heating up to 110 °C for 60 minutes. The result is the average of double testing. The result is calculated as:</p> $([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$				

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk/uncertainty.

Analytical results

Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
99.5	0 % **	0 %***	8.9	70 *

* VOC limit for "Multipurpose construction adhesives"

** Given by the client

*** No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Søren Ryom Villadsen
Contact Person

Morten Sielemann
Analytical Chemist